

## lick to Zoom In

# Does Your Flooring Have SUSTAINABLE Wet Slip Resistance?

BY GEORGE SOTTER, P.E., PH.D.

When an accident victim claims damages due to a fall on a slippery floor such as a wet pool deck, locker room floor, or tiled outdoor plaza - often the building service organization is named as a defendant.

The question arises as to whether the floor (a) was slippery when originally specified, and therefore unfit for its planned use; (b) was improperly maintained; or (c) became slippery from normal wear and tear. A test devised for McDonalds Restaurants and used by others such as Aldi, Toyota, Westfield, and a major cruise ship company helps determine this.

In safety engineering it is widely accepted that "safety by design" is the most reliable method of preventing accidents; people should not be expected reliably to use safety equipment (e.g. slip-resistant footwear) or exercise special caution ("Slippery [or wet]


floor" warnings). If flooring is in an area where it can get wet or otherwise lubricated (airborne deep-fryer fat, tracked-in grease, etc.), it needs to be slip-resistant under such conditions.

Although people sometimes assume that flooring slip resistance never changes with time, the experience of many building and cruise ship owners proves that this is not true. Wear from shoes plus abrasive soil on a busy floor, or certain inappropriate maintenance practices, can in some cases destroy the wet slip resistance in a matter of weeks or even an hour.

If a building owner can be confident that new flooring will sustain its slip resistance for a period of years, this can protect a considerable investment in the flooring and prevent business interruptions as well as protect the safety of the pedestrian. The stakes are even higher for hotels and cruise ships, which are occupied virtually nonstop with guests who will not tolerate the noise involved in changing out hard flooring.

# Test Methods and Safety Criteria

Germany and Australia have for over 10 years had detailed flooring slip resistance standards based on some 150 specific situations - e.g. external walkways, swimming pool decks, swimming pool stairs into the water, commercial kitchens, hospital operating rooms, etc. Many architects elsewhere in Europe have informally adopted them. The slip resistance ratings are based on humans walking an oily or water-wet flooring sample in standard footwear and/or bare feet on a laboratory variable-angle ramp. However, the test results generally apply only to flooring before it's installed. In some cases initially





CIRCLE 17 ON READER SERVICE CARD

CIRCLE 18 ON READER SERVICE CARD

good wet slip resistance is gone after the floor has been down for only a few weeks. What's more, the ramp test can't conveniently be used to assess safety of the flooring on site after installation or after a fall has occurred.

The United Kingdom has since 1971 had well-established slip resistance standards based on a portable test method.

The pendulum skid tester is now a stan-

dard test method for pedestrian slip resistance in 49 nations (European Committee for Standardization EN 13036-4, 2003 names many of them) on four continents and has been endorsed by Ceramic Tile Institute of America since 2001.

The SSR test procedure consists of an initial wet pendulum test; abrasion, wet, for up to several thousand cycles with a standard (3" x 3" 3M green Scotchbrite) abrasive pad under a standard load of 1 kg (2.2 lb) at 50 cycles per minute; and another wet pendulum test after abrasion. Either hard and soft rubber pendulum sliders (or "test feet") might be used if the area is walked on in both hard-bottom footwear and bare feet or soft-soled footwear.

Typically, about 85 percent of the loss in slip resistance after 5000 cycles has already occurred after 500 cycles. Depending on the flooring buyer's situation, the flooring might be considered to have Sustainable Slip Resistance for a level floor if, for example, the wet Pendulum Test Value (PTV) is 35 or higher after abrasion for 500 cycles. The 500-cycle result in the laboratory has been found by in situ pendulum tests to be roughly equivalent to 12-24 months of wear in customer areas at a busy McDonald's Restaurant. Mc-Donalds adopted the 500-cycle specification, minimum PTV of 35, in October 2006.

In some cases, analogous to the variableangle ramp test-related standards mentioned above, the SSR safety standards are situation-specific rather than "one size fits all." Thus a minimum pre-abrasion wet PTV of 35 (hard or soft slider) might be required for hotel or hospital bathroom floors; a minimum of 45 (hard rubber slider) for stair nosings that get wet in use; and 54 (hard slider) for commercial kitchens and steep outdoor ramps. For areas that normally remain dry, a minimum wet PTV of 12 or higher might be specified to allow for dust and tracked-in grease. If the flooring is to be sealed after installation, the laboratory tests must be conducted with the correct sealer properly

Experience has shown that what is specified and ordered is not always what is delivered, and it's prudent for building owners to verify that flooring meets their slip resistance specification both before installation and at turnover of the property for occupancy. For a busy floor, monitoring of dry and wet slip resistance every 3–12 months after that can further protect owner, building service, and other duty holders as well as guests and employees. FSM

George Sotter is president of Sotter Engineering Corporation. He has more than four decades of experience in rocket and jet propulsion and consulting engineering now specializing in slip and fall prevention and testing. He can be reached via email at George Sotter@SafetvDirectAmerica.com.





# MULTI-PURPOSE ABSORBENT

Spill Guard ECO is a unique absorbent for use in most applications. This combination absorbent is very easy to use, apply and pick up.

- WATER 40 times its weight
- OIL 2 times its weight
- ALCOHOL 3.75 times its weight
- BLEACH 2.75 times its weight



For a FREE DEMO KIT email <a href="mailto:Scott.Plasek@nch.com">Scott.Plasek@nch.com</a> today!

For more information contact Scott at 972-438-0697 see us at sqabsorbent.com

SPILLGUARD is a product of USA Packaging, Inc. A Division of NCH Corporation 2500 Carl Road | Irving, TX 75062 www.spabsorbent.com p: 972-438-0697 f: 972-721-6135

CIRCLE 19 ON READER SERVICE CARD